



INDUSTRIAL RAW MATERIALS LLC

39 West Mall, Plainview, NY 11803
T: (212) 688-8080 F: (212)-246-0158
irm@irmwax.com www.irmwax.com

INDRAWAX 51-AS

Petroleum Slack Wax

Test Results (these are also typical)

Property	Method ASTM	Test Result
Congealing point, °F (°C)	D-938	122 F° (50 C°)
Oil content, wt.%	D-721	13.2
Viscosity @ 212°F, cSt	D-445	3.6
Color, ASTM	D-1500	0.5
Flash point, °F (°C)	D-92	428 F° (220 C°)

- Availability: Liquid Bulk, Tank Cars or Tank Wagon
- Steadiness of Supply: Assured
- Variability of quality: Consistent
- Price: Competitive
- Contact: Guy Morra or Eddie Wu or Edgar Torres
- Phone/ E-mail: 212-688-8080 / irm@irmwax.com

